
## UniPhase 2000

### **Phase Change Interface Material**



**UniPhase 2000** is a phase changing thermal interface material, formulated to function as a superb alternative to messy and inconsistent thermal grease.

Supplied as a dry compound coated onto an aluminium substrate **UniPhase 2000** will flow at a phase change temperature of 60°C and conform to the differing surface textures between a heatsink and device. In combination with device mounting pressure and phase change flow, **UniPhase 2000** expels air voids at the interface helping to reduce thermal resistance. **UniPhase 2000** is supplied in die-cut preforms to suit a wide variety of electronic applications such as DC/DC power converters and is typically between any heat dissipating electrically isolated component and heatsink.

### **Features**

- Dry compound coated onto an aluminium substrate
- Above phase change temperature compound becomes thixotropic and paste-like in consistency
- Delivers a highly reliable and consistent thermal interface for demanding applications

### **Availability and Storage**

- Supplied in custom die-cut preforms and pads on sheets or rolls
- Available in a variety of thicknesses to suit individual application requirements
- Indefinite shelf life, within original packaging in conditions below 40°C

# Physical Properties (for a typical thickness)

Property (unit)	Test Method	UniPhase 2000
Total Thickness — includes compound and substrate (mm)	Visual	0.075
Max Operating Temp.(°C)	In House	+150
Thermal Impedance @ 20psi (°C-cm²/W)	ASTM D5470	0.2
Thermal Impedance @ 100psi (°C-cm²/W)	ASTM D5470	0.13

### **Benefits**

- Delivers a consistent and reliable thermal interface
- Mounting pressures and phase change flow expels air between uneven surfaces reducing thermal impedance
- Delivers a thin bond line between surfaces helping to improve thermal performance

### **Recommended Uses**


- Typically used to thermally connect an electrically isolated heat generating component to a heatsink
- · Within an application to replace thermal grease
- Power supplies and power modules

#### **Mechanical Properties**

Property (unit)	Test Method	UniPhase 2000
Phase Change Temperature (°C)	-	60
Volumetric Expansion upon phase-change (%)	In House	15%



www.universal-science.com
UK +44 (0) 1908 222 211



FR +33 (0) 1602 00276











